



**Dow Italia Divisione Commerciale s.r.l.**

Socio Unico  
Stabilimento di Correggio  
Via Carpi, 29 – 42015 Correggio (RE)  
Tel: +39 0522 6451  
Fax: +39 0522 645848

Correggio, 31<sup>st</sup> July 2023

Messrs

*DK Elementer A/S  
Stien 2  
7100 Vejle, Denmark*

**Subject:** *Test data on panels produced with CD 1200 Polyol by DK Elements*

Test	Standard	UoM	
Core Density	EN 1602	[kg/m <sup>3</sup> ]	32.27
Adhesion*	DOWM 120146-E05A	[kPa]	266.15
Compressive strength**	EN 826	[kPa]	149.68
Intial Lambda @ 10°C***	EN 13165	[mW/m.k]	22.35
Aged lambda @ 10°C, core foam 21 days @ 70°C***	EN 13165-C.5	[mW/m.k]	27.95

\* Average Value calculated on 5 samples

\*\* Average Value calculated on 8 samples in 3 directions

\*\*\* Average Value calculated on 2 samples

**Marco Callari**

Senior Sales Specialist  
Polyurethane Systems  
Dow Italia Divisione Commerciale

*All data, values, and information contained in the present document are purely indicative and, therefore, do not imply any responsibility or warranty on the part of Dow with respect to the performance of the product sold, its mode of application, as well as its use in the customer's manufacturing process. The tests do not imply as well any responsibility or warranty by Dow on the manufactured product made by the customer with the Dow product.*